

Physicochemical characteristics of fungal xylanases and their potential for biobleaching of kraft and non-wood pulps

ABSTRACT

Xylanases are enzymes with a wide variety of biotechnological applications, such as in the bioconversion of lignocellulosic materials, improvement of feed digestibility, and bleaching kraft pulps to increase pulp brightness. Many studies have been conducted and published over the years on cellulose pulp bleaching due to the need to search for more sustainable tools and thus reduce environmental pollution. Thus, in this review, we focus on analyzing the biochemical properties of xylanases produced by mesophilic and thermophilic fungi that have been used in the bleaching processes of kraft and non-wood pulps. *Eucalyptus* kraft pulp is still one of the most used raw materials in the production of pulp and paper, while straw and bagasse are alternative sources of non-wood pulps. Thermophilic fungal xylanases show optimum enzymatic activity at high temperatures and a shorter treatment period when compared to mesophilic xylanases in the bleaching step. However, mesophilic fungal xylanases exhibit a longer period of enzymatic treatment but achieve a satisfactory brightness and kappa number. Hence, these approaches will contribute to future applications of these xylanolytic enzymes in pulp and paper industries.

Keywords: Brightness, Cellulose, Fungus, Kraft, Xylanase.

1. INTRODUCTION

The pulp and paper industry is one of the most productive sectors in the world, stimulated by growing global demand. In Brazil, 7.84 million hectares of trees were planted in 2016, 34% of which belong to companies in the pulp and paper industry [1]. The industry is still growing – global paper production hit 400 million ton per year in 2014 – but it is traditionally known to contribute to environmental pollution, mainly due to its discharge of effluent [2]. The most significant environmental impact of the pulp and paper industry is caused by wastewater elimination, as producing one tonne of paper requires between 75 and 227 cubic metres of water [3].

Environmental regulation has increasingly restricted the use of chlorine compounds for the bleaching of kraft pulp, since the effluents produced by the industry contain a variety of organic and inorganic contaminants that mostly originate from tannins, lignin, resins, and chlorine compounds [4, 5]. Chlorinated organic compounds generated during the bleaching of pulp have been identified as toxic, mutagenic, and bioaccumulative. In addition, these chlorine compounds, even at low concentrations, may cause serious biological disorders [6, 7]. The pulp and paper industries have adapted to restrictions by using sustainability strategies that minimise their environmental impact. Elemental chlorine-free (ECF)

bleaching methods and enzymatic treatments have gained in popularity because of environmental concerns about the chlorinated compounds that are generated during the manufacture of cellulose.

In this context, numerous studies have been conducted by many researchers over the years to implement the use of enzymes as xylanases in kraft pulp pre-bleaching processes in order to use increasingly sustainable technologies. Thus, we focus on searching and analysing published data on the physicochemical characteristics of xylanases produced by various species of mesophilic and thermophilic fungi that have been tested in the bleaching processes of kraft and non-wood pulps in order to assist in the future application of these xylanolytic enzymes in pulp bleaching processes.

1.2 Use of Fungal Xylanase in Kraft Pulp Bleaching

In accordance with their commitment to expand their range of chlorine-free products, the paper industry has adopted enzymes as new, versatile tools. Viikari et al. (1986) [8] were the first to describe the use of enzymatic treatment to replace chlorine bleaching for the removal of lignin from wood pulp. Since the kraft bleaching process generates approximately 2 to 4 kg of organochlorine per tonne of pulp [9], the use of enzymes is a way to reduce the amount of chlorine dioxide required for pulp bleaching. Among the enzymes used, the xylanases are the most popular in the paper industry, where they are utilised as bleach boosting agents [10], reducing the chlorinated chemical volume by up to 25%. Consequently, a proportional reduction in the generation of chlorinated effluent has occurred [10]. Furthermore, when enzymatic pre-bleaching of eucalyptus and bagasse is supplemented with xylanase and laccase, the consumption of chlorine decreases by 20–25%, thereby reducing both the levels of pollutants in the final effluent and production costs [11].

The addition of xylanase during the bleaching step was one of the first reports on the efficient use of enzymes as a technological tool that could be added to an existing industrial plant without large investment. The xylanolytic system includes enzymes such as endo-1,4- β -xylanases (EC 3.2.1.8), β -xylosidases (EC 3.2.1.37), α -L-arabinofuranosidases (EC 3.2.1.55), α -D-glucuronidases (EC 3.2.1.139), acetyl xylan esterases (EC 3.1.1.72), and feruloyl esterases (EC 3.1.1.73) [12, 4]. Endo-1,4- β -xylanases (E.C.3.2.1.8) are the main glycosyl hydrolases (GH) of the xylanolytic system and are commonly called “xylanases”. The enzymes hydrolyse β -1,4 glycosidic bonds inside the xylan chain, producing xylooligosaccharides (XOS), and belong to the GH10 and GH11 families [13]. Xylan-1,4- β -xylosidases (E.C.3.2.1.37) act cooperatively with endo-1,4- β -xylanases, converting the xylooligosaccharides from the non-reducing end until D-xylose units and filamentous fungal β -xylosidases have been described only for families 3, 43, and 54 [14, 13]. However, many microorganisms, including filamentous fungi, yeast, and bacteria, are recognised producers of these xylanases [12].

Thus, the physicochemical properties of fungal xylanases as well as results obtained on the bleaching of pulps from studies carried out by several researchers are compiled in a table including treatment conditions for the bio-bleaching of cellulose pulp and *Eucalyptus* kraft pulp, treatment period, kappa number, and brightness (Table 1).

UNDER PEER REVIEW

Table 1. Physicochemical properties of fungal xylanases and their performance in pulp bleaching

Fungus	Xylanase (U/g pulp)	pH	Temperature (°C)	Treatment period (h)	Kappa number	Kappa efficiency (%)	Brightness (%)	Type of pulp	References
<i>Aspergillus flavus</i>	10	6.5	60	1	9.02	35.93	nr	<i>Eucalyptus</i> Kraft pulp	[15]
<i>Aspergillus flavus</i>	11	6.5	55	2	8.89	36.32	nr	<i>Eucalyptus</i> Cellulose pulp	[16]
<i>Aspergillus flavus</i>	10	6.5	55	2	2.56	18.34	nr	<i>Eucalyptus</i> Cellulose pulp	[17]
<i>Aspergillus fumigatus</i>	10	5.0 – 5.5	70	1	6.8	11.7	nr	<i>Eucalyptus</i> Cellulose pulp	[18]
<i>Aspergillus japonicus</i>	10	5,2	50	3	11.6	25.2	57.7	<i>Eucalyptus</i> Cellulose pulp	[19]
<i>Aspergillus niger</i>	10	6.5	55	2	10.34	25.93	nr	<i>Eucalyptus</i> Cellulose pulp	[16]
<i>Aspergillus niger</i>	35	5.5	55	2	7.4	14.9	59.6	<i>Eucalyptus</i> Cellulose pulp	[20]
<i>Aspergillus niger</i>	5	7	50	4	4.8	nr	70.8	Cellulose pulp	[21]
<i>Aspergillus niger</i>	60	nr	50	2	19.9	nr	41.8	Paper pulp	[22]
<i>Aspergillus niveus</i>	10	4.5 – 5.0	65	1	7.1	39.6	58.1	<i>Eucalyptus</i> Cellulose Kraft	[18]
<i>Aspergillus niveus</i>	35	5.5	55	2	6.9	20.7	59.6	Cellulose pulp	[20]
<i>Aspergillus ochraceus</i>	35	5.5	55	2	6.9	20.7	58.9	Cellulose pulp	[20]

<i>Aspergillus ochraceus</i>	10	5	65	1	7.5	36.4	57.1	Cellulose pulp	[24]
<i>Aspergillus oryzae</i> NRRL 1808	51	6.0	60	nr	nr	nr	1.4	Eucalyptus pulp	[25]
<i>Aspergillus sydowii</i> SBS 45	25	8.2	40	5	14.32	nr	41	Kraft pulp	[26]
<i>Aspergillus terricola</i>	10	6.5	60	1	6.6	14.3	60.3	<i>Eucalyptus</i> Cellulose pulp	[24]
<i>Penicillium corylophilum</i>	5	7	50	4	4.9	nr	73	<i>Eucalyptus</i> Cellulose Kraft	[21]
<i>Penicillium crustosum</i>	25	5.5	50	2	9.77	nr	nr	<i>Eucalyptus</i> Cellulose Kraft	[27]
<i>Penicillium janczewskii</i>	2	5.5	50	1	<3	nr	nr	<i>Eucalyptus</i> Kraft pulp	[28]
<i>Penicillium sp</i>	20	nr	30	1	2.3	nr	0.9	Waste office paper	[29]
<i>Thermomyces lanuginosus</i> CBS 288.54	40	7.0 – 7.5	70 - 75	1	nr	nr	66.91	Wheat straw pulp	[30]
<i>Thermomyces lanuginosus</i> wild type	10	7	60	1.5	nr	8.6	2.63	Wheat straw pulp	[31]
<i>Thermomyces lanuginosus</i> mutant (M7)	10	8	65	1.5	2.29	18.6	nr	Wheat straw pulp	[31]
<i>Thermomyces lanuginosus</i> SSBP	50	6.5	50	3	9	nr	46.1	Bagasse pulp	[32]
<i>Trichoderma asperellum</i>	100	5.0	50	1	4.2	nr	4	Paper pulp	[33]

<i>Trichoderma longibrachiatum</i>	5	7	50	4	4.3	nr	71.6	Cellulose kraft pulp from <i>Eucalyptus</i>	[21]
<i>Trichoderma viride</i>	10	6	60	1	12.99	nr	nr	Kraft pulp from <i>Eucalyptus</i>	[34]

Nr: not related

The bleaching of cellulose pulp, *Eucalyptus* kraft, or non-wood pulp has been supplemented with xylanases from both mesophilic and thermophilic fungi. *Eucalyptus* pulp is one of the most commonly used pulps in paper production, while wheat straw represents a common source of alternative raw material or non-wood pulp. Xylanases produced by thermophilic fungi such as *Aspergillus fumigatus* and *Thermomyces lanuginosus* show optimum enzymatic activity at high temperatures (70–75 °C), but the treatment period with xylanase is shorter (0.5 h), an important factor in reducing cost in the bleaching process. In contrast, mesophilic fungal xylanases show optimum activity in the range of 50–55°C and acidic pH (5.0–6.5), require a longer enzyme treatment period (2–4 h) to achieve a satisfactory brightness, and have a lower kappa number. According to the properties of the enzyme, a neutral or alkaline pH also improves pulp bleaching, with a 70.8% increase in brightness at pH 7.0 [21]. Similarly, xylanases with an optimum pH of 7.0 from the fungi *Penicillium corylophilum* and *Trichoderma longibrachiatum* produced an increase in brightness of 73% and 71.6%, respectively [21].

Other hemicellulases, such as ferulic acid esterases and galactosidases, have also been reported to help in the bleaching of cellulose pulp with xylanases [4]. While lipases are generally applied during the processing of the paper, xylanase and laccase are more commonly used in the bleaching and delignification processes [35]. The benefits of enzymatic treatment include a reduction of operating costs and organic pollutants, improvement in the brightness and properties of the pulp, reduction of the kappa number, and increase in fibre yield [36]. In addition, bio-bleaching of non-wood kraft pulps (rice straw, wheat straw, bagasse, etc.) treated with *T. lanuginosus* SSBP xylanase released chromophores and organic halogens, reduced sugars, and decreased the kappa number [37].

Several hypotheses have been proposed to explain the role of cellulase-free xylanase in the bleaching of paper pulp: the treatment of cellulose pulp with cellulase-xylanase helps and improves the infiltration of bleaching chemicals, breaking down the xylan structure, and consequently removes the lignin-based chromophores from the cellulose fiber [8, 38, 39, 40]. Some studies have shown that pre-bleaching with xylanase is an innovative and environmentally friendly, as well as inexpensive, method that can decrease the amount of chemicals needed to achieve a given brightness in the later stages of chemical treatment. Therefore, pre-treatment with xylanases increases the efficiency of the chemical extraction of lignin from pulp and further minimises the need for chlorine dioxide (ClO₂) [41, 42]. Thus, a significant number of pulp and paper industries in Europe, North America, South America, and Japan have used enzymes in the kraft bleaching processes. North America has already improved the processing of 2.5 million tonnes of pulp using xylanase in the pre-bleaching steps [43].

2. CONCLUSION

Eucalyptus kraft pulp is still the most reported among pulp and paper production, while wheat straw represents a source of alternative raw material or non-wood pulp. The bleaching of *Eucalyptus* kraft or non-wood pulps by both mesophilic and thermophilic fungal xylanases has been studied. Thermophilic fungal xylanases have shown optimum enzymatic activity at high temperatures, an advantage because they require a shorter treatment period, which reduces operational cost. On the other hand, mesophilic fungal xylanases are effective in achieving satisfactory results in brightness and a lower kappa number, but they require a longer treatment time compared to thermophilic fungal xylanase. Thus, these approaches will contribute to future applications of these xylanolytic enzymes in pulp and paper industries.

REFERENCES

1. Brazilian Tree Industry – Report 2017 - Indústria Brasileira de Árvores (IBÁ) http://iba.org/images/shared/Biblioteca/IBA_RelatorioAnual2017.pdf 2017. Portuguese.
2. Skals PB, Krabek A, Nielsen PH, Wenzel H. Environmental assessment of enzyme as-sisted processing in pulp and paper industry. *Int J LCA*. 2008;13:124–132. <http://dx.doi.org/10.1065/lca2007.11.366>.
3. Pokhrel D, Viraraghavan T. Treatment of pulp and paper mill wastewater- a review. *Sci Total Environ*. 2004; 333: 37-58. <https://doi.org/10.1016/j.scitotenv.2004.05.017>
4. Polizeli ML, Rizzatti AC, Monti R, Terenzi HF, Jorge JA, Amorim DS. Xylanases from fungi: properties and industrial applications. *J Appl Microbiol Biochem*. 2005; 67:577-91. doi: 10.1007/s00253-005-1904-7
5. Ashrafi O, Yerushalmi L, Haghighat F. Wastewater treatment in the pulp-and-paper industry: A review of treatment processes and the associated greenhouse gas emission. *J Environ Manage*. 2015; 158:146-157. doi: 10.1016/j.jenvman.2015.05.010
6. Onysko K A. Biological bleaching of chemical pulps: A review. *Biotechnol Adv*. 1993; 11: 179-198. [https://doi.org/10.1016/0734-9750\(93\)90040-T](https://doi.org/10.1016/0734-9750(93)90040-T)
7. Dedhia B S, Vetal M D, Rathod V K, Levente C. Xylanase and laccase aided bio-bleaching of wheat straw pulp. *Can J Chem Eng*. 2014; 92:131-138. <https://doi.org/10.1002/cjce.21798>
8. Viikari L, Ranua M, Kantelinen A, Sundquist J, Linko M. Bleaching with enzymes(1986) *In: 3rd International Conference on Biotechnology in the Pulp and Paper Industry in Stockholm*
9. Kansal SK, Singh M, Sud D. Effluent quality at Kraft/soda agro-based paper mills and its treatment using a heterogeneous photocatalytic system. *Desalination*. 2008;228:183–190. <https://doi.org/10.1016/j.desal.2007.10.007>
10. Bajpai P, Anand A, Bajpai P K. Bleaching with lignin-oxidizing enzymes. *Biotechnol Annu Rev*. 2006; 12:349-378. doi: 10.1016/S1387-2656(06)12010-4
11. Thakur V V, Jain R K, Mathur RM. Studies on xylanase and laccase enzymatic prebleaching to reduce chlorine-based chemicals during CEH and ECF bleaching. *BIORESOURCES*. 2012; 7: 2220-2235. doi: 10.15376/biores.7.2.2220-2235
12. Beg QK, Kapoor M, Mahajan L, Hoondal GS. Microbial xylanases and their industrial applications: a review. *Appl Microbiol Biotechnol*. 2001;56:326-338. doi: 10.1007/s002530100704
13. Heinen PR, Betini JHA, Polizeli MLTM. Xylanases, in: *Reference Module in Life Sciences*, Elsevier, 2017;1-12.
14. Knob A, Terrasan CRF, Carmona EC. β -Xylosidases from filamentous fungi: an overview. *World J Microbiol Biotechnol*. 2010; 26: 389-407. <http://dx.doi.org/10.1007/s11274-009-0190-4>
15. Martins MD, Guimarães MW, Lima VA, Gaglioti AL, Da-Silva PR, Kadowaki M K, Knob A. Valorization of passion fruit peel by-product: Xylanase production and its potential as bleaching agent for kraft pulp *Biocatal Agric Biotechnol*. 2018; 172-180
16. de Alencar Guimaraes N, Sorgatto M, Peixoto-Nogueira SD, Betini JH, Zanoelo F, Marques M, Polizeli M LTM, Giannesi GC. Bioprocess and biotechnology: effect of xylanase from *Aspergillus niger* and *Aspergillus flavus* on pulp biobleaching and enzyme production using agroindustrial residues as substract. *SPRINGERPLUS*. 2013; 2: 1. doi: 10.1186/2193-1801-2-380

17. da Silva PO, Guimarães NCA, Peixoto-Nogueira SC, Betini JH, Marchetti C R, Zanoelo FF, Polizeli MLTM, Marques MR, Giannesi G C. Production of cellulase-free xylanase by *Aspergillus flavus*: Effect of polyols on the thermostability and its application on cellulose pulp biobleaching. *Afr J Biotechnol.* 2015; 14:3368-3373. doi: 10.5897/AJB2015.14943
18. Peixoto-Nogueira SD, Michelin M, Betini JHA, Jorge JA, Terenzi HF, Polizeli MLTM. Production of xylanase by *Aspergilli* using alternative carbon sources: application of the crude extract on cellulose pulp biobleaching. *J Ind Microbiol Biotechnol.* 2009; 36:149- 149-155. <https://doi.org/10.1007/s10295-008-0482-y>
19. Guimarães NCA, Sorgatto M, Peixoto-Nogueira SC, Betini JHA, Zanoelo FF, Marques M, Polizeli MLTM, Giannesi GC. Xylanase Production from *Aspergillus japonicus* var *aculeatus*: Production using Agroindustrial Residues and Biobleaching Effect on Pulp. *J Biocatal Biotransformation.* 2013; 2:1. doi:10.4172/2324-9099.1000105
20. Betini JHA, Michelin M, Peixoto-Nogueira SC, Jorge JA, Terenzi HF, Polizeli MLTM. Xylanases from *Aspergillus niger*, *Aspergillus niveus* and *Aspergillus ochraceus* produced under solid-state fermentation and their application in cellulose pulp bleaching. *Bioprocess Biosyst Eng.* 2009; 32:819-824. doi: 10.1007/s00449-009-0308-y.
21. Medeiros RG, Da Silva JrFG, Bão SN, Hanada R, Ferreira Filho EX. Application of xylanases from amazon forest fungal species in bleaching of eucalyptus kraft pulps. *Braz Arch Biol Technol.* 2007; 50:231-238. <http://dx.doi.org/10.1590/s1516-89132007000200008>
22. Sridevi A, Sandhya A, Ramanjaneyulu G, Narasimha G, Devi PS. Biocatalytic activity of *Aspergillus niger* xylanase in paper pulp biobleaching. *3 Biotech.* 2016;6(2):165 doi: 10.1007/s13205-016-0480-0
23. Peixoto-Nogueira S D,. Michelin M, Betini JHA, Jorge J A, Terenzi HF,. Polizeli MLTM, Production of xylanase by *Aspergilli* using alternative carbon sources: application of the crude extract on cellulose pulp biobleaching. *J Ind Microbiol Biot.* 2009;36:149-155.
24. Michelin M, Peixoto-Nogueira SC, Betini JHA, da Silva TM, Jorge JA, Terenzi H, Polizeli MLTM. Production and properties of xylanases from *Aspergillus terricola* Marchal and *Aspergillus ochraceus* and their use in cellulose pulp bleaching. *Bioproc Biosyst Eng.* 2009;33(7):813-821.
25. Szendefy J, Szakacs G, Christopher L. Potential of solid-state fermentation enzymes of *Aspergillus oryzae* in biobleaching of paper pulp. *Enzyme Microb Tech.* 2006; 39(6): 1354-1360
26. Nair SG, Sindhu R, Shashidhar S. Enzymatic bleaching of kraft pulp by xylanase from *Aspergillus sydowii* SBS 45. *Indian J. Microbiol.* 2010;50(3):332-328.
27. Silva NFS, Simões MR, Knob A, Moraes SS, Henn C, Silva JLC, Simão RCG, Maller A, Kadowaki MK. Improvement in the bleaching of Kraft pulp with xylanase from *Penicillium crustosum* FP 11 isolated from the Atlantic forest. *Biocatal Biotransformation.* 2016; 34:119-127. doi: 10.1080/10242422.2016.1212849.
28. Terrasan CRF, Temer B, Sarto C, Silva Junior FG, Carmona EC. Xylanase and β -xylosidase from *Penicillium janczewskii*: Production, physico-chemical properties, and application of the crude extract to pulp biobleaching. *BIORESOURCES.* 2013; 8:1292-1305. doi: 10.15376/biores.8.1.1292-1305
29. Sridevi A, Narasimha G, Devi PS. Production of xylanase by *Penicillium* sp. And its biobleaching efficiency in paper and pulp industry. *Int. J Pharm Sci Rev Res.* 2019; 10(3): 1307-1311
30. Li X, Jiang Z, Li L, Yang SQ, Feng WY, Fan JY, Kusakabe I. Characterization of a cellulase-free, neutral xylanase from CBS 288.54 and its biobleaching effect on wheat straw pulp. *Bioresour. Technol.* 2005; 96: 1370-1379. doi:10.1016/j.biortech.2004.11.006
31. Bokhari SAI, Rajoka MI, Javaid A, Shafiq-ur-Rehman , Ishtiaq-ur-Rehman, Latif F. Novel thermodynamics of xylanase formation by a 2-deoxy-d-glucose resistant mutant of *Thermomyces lanuginosus* and its xylanase potential for biobleachability. *Bioresour. Technol.* 2010; 101:2800-2808. <https://doi.org/10.1016/j.biortech.2009.10.072>

32. Manimaran A, Kumar KS, Permaul K, Singh S. Hyper production of cellulase-free xylanase by *Thermomyces lanuginosus* SSBP on bagasse pulp and its application in biobleaching. *Appl Microbiol Biotechnol.* 2008; 81:887-893. doi: 10.1007/s00253-008-1693-x
33. Sridevi A, Ramanjaneyulu G, Suvarnalatha, Devi PS. Biobleaching of paper pulp with xylanase produced by *Trichoderma asperellum*. *3 Biotech.* 2017;7(4):266. doi: 10.1007/s13205-017-0898-z.
34. Fortkamp D, Knob A. High xylanase production by *Trichoderma viride* using pineapple peel as substrate and its application in pulp biobleaching. *Afr. J. Biotechnol.* 2014;13:2248-2259. doi: 10.5897/AJB2013.13479
35. Demuner BJ, Junior NP, Antunes AMS. Technology prospecting on enzymes for the pulp and paper industry. *JOTMI.* 2011; 6:148-158. <http://dx.doi.org/10.4067/s0718-27242011000300011>
36. Gangwar A K, Prakash N T, Prakash R. Applicability of microbial xylanases in paper pulp bleaching: A review. *BIORESOURCES.* 2014; 9: 3733-3754. doi: 10.15376/biores.9.2.3733-3754
37. Ziaie-Shirkolaee Y, Talebizadeh A, Soltanali S. Comparative study on application of *T. lanuginosus* SSBP xylanase and commercial xylanase on biobleaching of non-wood pulps. *Bioresour Technol.* 2008; 99:7433–7437. doi: 10.1016/j.biortech.2008.02.032.
38. Viikari L, Kantelinen A, Sundquist J, Linko M. Xylanases in bleaching: from an idea to the industry. *FEMS Microbiol Rev.* 1994; 13:335-350. <https://doi.org/10.1111/j.1574-6976.1994.tb00053.x>
39. Walia A, Mehta P, Guleria S, Shirkot CK. Modification in the properties of paper by using cellulase-free xylanase produced from alkalophilic *Cellulosimicrobium cellulans* CKMX1 in biobleaching of wheat straw pulp. *Can J Microbiol.* 2015; 61:671-681. doi: 10.1139/cjm-2015-0178.
40. Kumar A, Gautam A, Dutt D, Yadav M, Sehrawat N, Kumar P. Applications of microbial technology in the pulp and paper industry. In book - *Microbiology and Biotechnology.* Publisher: Nova Science Publishers, New York, USA, Editors: Vikas Kumar, Gulab Singh, Neeraj K. Aggarwal, 2017;185-206
41. Khonzue P, Laothanachareon T, Rattanaphan N, Tinnasulanon P, Apawasin S, Paemanee A et al. Optimization of xylanase production from *Aspergillus niger* for biobleaching of eucalyptus pulp. *Biosci Biotechnol Biochem.* 2011;75:1129–1134. <https://doi.org/10.1271/bbb.110032>
42. Walia A, Guleria S, Mehta P, Chauhan A, Parkash J. Microbial xylanases and their industrial application in pulp and paper biobleaching: a review. *3 Biotech.* 2017; 7: 11 doi: 10.1007/s13205-016-0584-6.
43. Nguyen D, Zhang X, Jiang ZH, Audet A, Paice MG, Renaud S, Tsang A. Bleaching of Kraft pulp by a commercial lipase: Accessory enzymes degrade hexenuronic acids. *Enzyme Microb Tech.* 2008; 43:130-136. doi: 10.1016/j.enzmictec.2007.11.012